



ZENITH INDUSTRIAL RUBBER PRODUCTS PVT. LTD.

Quality Rubber Solutions

An ISO 9001:2008 Registered Company
An ISO 14001: 2004 Registered Company

GOVT.RECOGNISED EXPORT HOUSE

TECHNICAL SPECIFICATIONS

QUALITY : COMMERCIAL NATURAL RUBBER CODE: NR 65135

PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUES
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.35 ± 0.05	ASTM D297	1.35 ± 0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH (min)	DIN 53504	710 PSI	ASTM D412	50 kg/cm2
ELONGATION AT BREAK (min)	DIN 53504	300%	ASTM D412	300%
ABRASION RESISTANCE (max)	DIN 53515	300 mm3	ASTM D5963	300 mm3
COMPRESSION SET (70°C/24 hrs/25% set) (max)	DIN 53508	50%	ASTM D395 METHOD B	50%
TEAR RESISTANCE (Angular) min	DIN 53505	123 Lbs/Inch	ASTM D624	22 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING (72 hrs. AT 70°C)			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / -25		+ 10 / -25
--- ELONGATION AT BREAK (%)		+ 10 / -25		+ 10 / -25
VOLUME SWELL : AT 70°C FOR 72 HRS/IN			ASTM D 471	
IRM OIL NO.1		NOT RECOMMENDED		NOT RECOMMENDED
IRM OIL NO.2		NOT RECOMMENDED		NOT RECOMMENDED
IRM OIL NO.3		NOT RECOMMENDED		NOT RECOMMENDED
CHEMICAL RESISTANCE				
--- OZONE		NOT RECOMMENDED	ASTM D 1149	NOT RECOMMENDED
--- DILUTE ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30° to + 70 °C		-30° to + 70 °C
COLOUR		BLACK		BLACK



141/144,14TH FLOOR, FREE PRESS HOUSE, FREE PRESS JOURNAL MARG 215,NARIMAN POINT MUMBAI - 400021

Email: info@zenithrubber.com

Website: www.zenithrubber.com